

Data sheet

31.10.2022

Filter paper

Parameter*	Value*
Grade	MN 640 m
Basis weight	85 g/m ²
Thickness	0.2 mm
Filtration speed	27 s
Surface	smooth
Ash content	<0.01 %
Average retention capacity	4-12 µm
Characteristics / Application	Ashless, medium fast filtration, e.g. for sulphides, lead chromate, calcium oxalate

*These data are typical values and must not be regarded as specification.



MACHEREY-NAGEL GmbH & Co. KG
 Valencienner Str. 11
 52355 Düren · Germany
www.mn-net.com

DE Tel.: +49 24 21 969-0 info@mn-net.com
 CH Tel.: +41 62 388 55 00 sales-ch@mn-net.com
 FR Tel.: +33 388 68 22 68 sales-fr@mn-net.com
 US Tel.: +1 888 321 62 24 sales-us@mn-net.com