

## Data sheet

31.10.2022

## Filter paper

Parameter*	Value*
Grade	MN 640 w
Basis weight	85 g/m <sup>2</sup>
Thickness	0.2 mm
Filtration speed	9 s
Surface	smooth
Ash content	<0.01 %
Average retention capacity	7-12 µm
Characteristics / Application	Ashless, fast filtration, for coarse precipitates e.g. iron- and aluminium- hydroxide, bismuth-, copper- and iron-sulphide, nickel diacetyldioxime

\*These data are typical values and must not be regarded as specification.



MACHEREY-NAGEL GmbH & Co. KG  
 Valencienner Str. 11  
 52355 Düren · Germany  
[www.mn-net.com](http://www.mn-net.com)

DE Tel.: +49 24 21 969-0 [info@mn-net.com](mailto:info@mn-net.com)  
 CH Tel.: +41 62 388 55 00 [sales-ch@mn-net.com](mailto:sales-ch@mn-net.com)  
 FR Tel.: +33 388 68 22 68 [sales-fr@mn-net.com](mailto:sales-fr@mn-net.com)  
 US Tel.: +1 888 321 62 24 [sales-us@mn-net.com](mailto:sales-us@mn-net.com)