

## Data sheet

31.10.2022

## Filter paper

Parameter*	Value*
Grade	MN 728
Basis weight	170 g/m <sup>2</sup>
Thickness	0.4 mm
Filtration speed	55 s
Surface	smooth

Characteristics / Application      Slow filtration, with about 30% activated charcoal for discoloring colored liquids, e.g. for electroplating baths

\*These data are typical values and must not be regarded as specification.



MACHEREY-NAGEL GmbH & Co. KG  
 Valencienner Str. 11  
 52355 Düren · Germany  
[www.mn-net.com](http://www.mn-net.com)

DE Tel.: +49 24 21 969-0    info@mn-net.com  
 CH Tel.: +41 62 388 55 00    sales-ch@mn-net.com  
 FR Tel.: +33 388 68 22 68    sales-fr@mn-net.com  
 US Tel.: +1 888 321 62 24    sales-us@mn-net.com