

## Data sheet

31.10.2022

## Filter paper

| Parameter*                    | Value*   |
|-------------------------------|--|
| Grade                         | MN GF-3  |
| Basis weight                  | 50 g/m <sup>2</sup>  |
| Thickness                     | 0.28 mm  |
| Filtration speed              | 25 s   |
| Surface                       | smooth   |
| Average retention capacity    | 0.6 µm   |
| Maximum temperature           | 500 °C   |
| Characteristics / Application | Glass fiber filter without binder, e.g. for laboratory filtration and air sampling |

\*These data are typical values and must not be regarded as specification.



MACHEREY-NAGEL GmbH & Co. KG  
 Valencienner Str. 11  
 52355 Düren · Germany  
[www.mn-net.com](http://www.mn-net.com)

DE Tel.: +49 24 21 969-0 [info@mn-net.com](mailto:info@mn-net.com)  
 CH Tel.: +41 62 388 55 00 [sales-ch@mn-net.com](mailto:sales-ch@mn-net.com)  
 FR Tel.: +33 388 68 22 68 [sales-fr@mn-net.com](mailto:sales-fr@mn-net.com)  
 US Tel.: +1 888 321 62 24 [sales-us@mn-net.com](mailto:sales-us@mn-net.com)